

OYT is a water-based emulsion composed of acrylic polymers and selected ingredients which is specially designed for water tanks.

PRODUCT CHARACTERISTICS

| PROPERTIES | SPECIFICATIONS |
|------------------|-----------------------|
| Nature | Smooth paste |
| Colour | Cow dung colour |
| Specific gravity | |
| @ 27°C | 1.40 ± 0.05 |
| Non-volatile | |
| content | 55.00 ± 5.00% |
| Viscosity | 3000 - 5000 cP |
| pH | 8.00 ± 1.00 |
| Finish | Rich matt |
| Surface dry | 30 minutes |
| Over coating | |
| interval | 4 - 6 hours |
| Stability | |
| of thinned paint | 24 hours |

USES

Water tanks, septic tanks | Swimming pools.

BENEFITS

Alternate to chlorinated rubber paint | Environment friendly | Advanced formulation to arrest water leakage | Elastomeric flexible coating

| Excellent resistance to ingress of water | Non toxic

I Safe for potable water.

SHELF LIFE & STORAGE

Best before 12 months in an unopened, undamaged, originally sealed packing and if stored in dry conditions
I Protect from direct sunlight.
RECOMMENDED DOSAGE
400 ml of water per litre of OYT.

COVERAGE 100 – 110 sq.ft / litre / coat.

100 – 110 sq.ft / litre / coat

All surfaces must be clean, dry and free of dirt, chalk, grease, wax, rust and loose or peeling paint before painting I Apply one coat of Veco Primer and allow it to dry for 4-6 hours I Dilute with 40% of water by volume to OYT and stir thoroughly to get homogenous mixture I Apply single coat and allow it to dry for about 4-6 hours I After 4-6 hours, apply another coat.

NOTE

Do not apply on wet tanks

I Ambient and surface temperatures must be between 5°C and 40°C during application.

HEALTH & SAFETY PREGAUTIONS

Use rubber hand gloves & safety goggles In case of contact with skin,

wash with plenty of water Keep out of reach of children.

PACKAGING







